

## SATEN PRO

It is a white cement based, polymer added, thin satin plastering material applied on rough plaster.

### ■ ADVANTAGES

- It is easy and fast to apply.
- It does not cause dust or cracking.
- Provides high adherence to the surface on which it is applied.
- It provides a smooth surface by being easily sanded.
- Working time is long.
- It is resistant to external climatic conditions.

### ■ SCOPE OF APPLICATION

- It is used in interior and exterior areas, in repairs before painting, and in closing cracks and pores on surfaces.

### ■ WARNINGS AND RECOMMENDATIONS

- The application surface must be dry, clean and solid.
- Ambient temperature at the time of application and the next 24 hours should be between +5°C and +35°C.
- Foreign material should not be added to the mixture.
- Single coat application should be max 1.5 mm.

### ■ STORAGE

Packaging	20 kg Kraft Bag
Colour	White
Shelf Life	1 year from date of manufacture when stored unopened and undamaged in a dry, moisture-free environment. Packages should be kept tightly closed when not in use.

### ■ CONSUMPTION

0.90-1.10 kg/m<sup>2</sup> - for 1 mm application

### ■ APPLICATION FEATURES

- DRYFIX SATEN PRO fine plaster material should be slowly added into 7,00-8,00 liters of clean water. With the help of a mixer, at low speed, the product should be slowly added to the water and mixed for 2-3 minutes until it becomes homogeneous.
- The mixture is left to rest for 5 minutes and mixed again for 1-2 minutes to make it ready for use.
- The prepared mixture should be consumed within 1-2 hours.
- After complete drying, the surface is sanded to obtain a smooth surface.

All technical information stated in this product data sheet is based on laboratory tests.  
Actual values may vary due to circumstances beyond our control.

### İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 Işıkkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35



## SATEN PRO

### ■ TECHNICAL SPECIFICATIONS AND PERFORMANCE VALUES

Product Structure	Cement- based powder
Colour	White
Water Mixing Ratio	7,00-8,00 L water / 20 kg
Time To Wait Between Coats	2-3 hours
Compressive Strength	≥15 N/mm <sup>2</sup>
Bond Strength	≥1,0 N/mm <sup>2</sup>
Reaction to Fire Class	A1

The stated times apply for 20°C substrate and ambient temperature; increase at lower temperatures and decrease at higher temperatures. DryFiX is not responsible for the application errors arising from use of product beyond its intended purpose of failure to comply with the forgoing application conditions and advice on the product.

### ■ SAFETY PRECAUTIONS

During use and storage, appropriate work clothes, glasses, gloves and masks should be used for worker health and safety. Eye, mouth and skin contact should be avoided. The contacted area should be washed with plenty of water. In more dangerous situations or if the product is swallowed, a specialist doctor should be consulted immediately. Food and drink should not be allowed into application areas. It should be kept out of reach of children. For detailed information, the Safety Data Sheet (SDS) should be consulted.

### ■ LEGAL WARNING

Applications that may occur if the product is used for purposes other than its intended purpose or if the above-mentioned conditions are not complied with: from the mistakes of İzersan Yapı Malz. San. VE TİC. LTD. ŞTİ. is not responsible.

All technical information stated in this product data sheet is based on laboratory tests. Actual values may vary due to circumstances beyond our control.

### İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 Işikkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35

