Issue Date: 01.02.2024 Revision No: 001

SELF PRO

Cement-based, self-leveling leveling screed that can be applied in 1-10 mm thickness, contains modified additives, has high abrasion and pressure resistance.

ADVANTAGES

- It is applied easily and quickly.
- It has high resistance to pressure, abrasion and cracking.
- It offers a homogeneous and smooth surface.
- It can be used safely in the range of 1-10 mm.
- · Spreading performance is high.

SCOPE OF APPLICATION

 Indoors, in shopping malls open to light pedestrian traffic, on floors with bite from the ground, under parquet and laminate-like coatings.

■WARNINGS AND RECOMMENDATIONS

- Not applicable on metal surfaces.
- Absolutely foreign materials should not be added.
- The application surface must be free of dirt and dust, and must be clean, dry, smooth and solid.
- Weak areas and deep cracks on the surface should be repaired with SET RP 1320 repair mortar 24 hours before.
- The surface must be primed with floor primer at least 2 hours before.
- In areas with high air circulation, application should not be made in cases where there is a possibility of frost formation within 24 hours after application.
- Laminate, parquet and PVC coatings, min. It should be done after 48 hours.
- $(+5 \degree C)$ $(+35 \degree C)$ degrees is recommended.
- All tools used after the application should be washed with water before drying.

STORAGE

Packaging	25 kg Kraft Bag
Colour	Grey
Shelf Life	1 year from date of manufacture when stored unopened and undamaged in a dry, moisture-free environment. Packages should be kept tightly closed when not in use.

■ CONSUMPTION

 $1.9-2.1 \, \text{kg/m}^2 - 1 \, \text{mm}$

APPLICATION FEATURES

- 25 kg bag with 5.75-6.25 lt of clean water, with the help of a mixer at low speed, the product is slowly added to the water and mixed for 2-3 minutes until it becomes homogeneous. The product should be rested for 1-2 minutes before the application.
- The mixture is poured on the floor and allowed to spread. However, a trowel or squeegee can be used to increase the spreading speed.
- After spreading, the surface is leveled with the help of a spiked roller.

All technical information stated in this product data sheet is based on laboratory tests. Actual values may vary due to circumstances beyond our control.

İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 lşıkkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35



Issue Date: 01.02.2024 Revision No: 001

SELF PRO

■ TECHNICAL SPECIFICATIONS AND PERFORMANCE VALUES

Product Structure	Cement- based powder
Colour	Grey
Water Mixing Ratio	5.75-6.25 L water / 25 kg
Application Thickness	1-10mm
Full Installation and Service Time	min 24 hours
Mortar Usage Period	Max 45 min
Reference Standard	TS EN 13813
Sub-Adhesive Strength	≥ 1 N/mm²
Pressure strength	≥ 20 N/mm²
Flexural Strength	≥ 5 N/mm²
Soluble Chlorine content	≤ 0.05%
Reaction to Fire Class	A1

The stated times are valid at 20°C surface and ambient temperature, the time is extended at low temperatures and shortened at high temperatures. DRYFIX is one of the application errors that may occur if the product is used out of its intended use or if the above-mentioned application conditions and recommendations are not followed. Insulation is not responsible.

■ SAFETY PRECAUTIONS

During use and storage, appropriate work clothes, glasses, gloves and masks should be used for worker health and safety. Eye, mouth and skin contact should be avoided. The contacted area should be washed with plenty of water. In more dangerous situations or if the product is swallowed, a specialist doctor should be consulted immediately. Food and drink should not be allowed into application areas. It should be kept out of reach of children. For detailed information, the Safety Data Sheet (SDS) should be consulted.

■ LEGAL WARNING

Applications that may occur if the product is used for purposes other than its intended purpose or if the above-mentioned conditions are not complied with: from the mistakes of İzersan Yapı Malz. San. VE TİC. LTD. ŞTİ. is not responsible.

All technical information stated in this product data sheet is based on laboratory tests. Actual values may vary due to circumstances beyond our control.

İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 lşıkkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35

