

SHOCK

Cement-based, very fast-setting, water-blocking mortar used for active water leaks and their repairs.

■ ADVANTAGES

- It is easy and fast to apply.
- It prevents water leakage by setting immediately after contact with water.
- It does not cause dust or cracking.
- Provides high adherence to the surface on which it is applied.
- It is resistant to external climatic conditions.

■ SCOPE OF APPLICATION

- It is used indoors and outdoors, on all cement-based surfaces with water leakage such as foundations, basements, water tanks and pools.

■ WARNINGS AND RECOMMENDATIONS

- It is not applied to surfaces such as metal, wood, brick and plastic.
- It does not provide full protection at the point of water leakage, weak parts and areas with possible movement potential.
- Ambient temperature at the time of application and the next 24 hours should be between +5°C and +35°C.
- Foreign material should not be added to the mixture.

■ STORAGE

Packaging	5kg plastic bucket
Colour	Grey
Shelf Life	1 year from date of manufacture when stored unopened and undamaged in a dry, moisture-free environment. Packages should be kept tightly closed when not in use.

■ APPLICATION FEATURES

- Gloves must be used before application.
- DRYFIX SHOCK material is taken in the palm and applied to the area with water leakage and pressure is applied with the palm for 5-10 seconds.
- Take some DRYFIX SHOCK material into the palm again and rub and plaster the applied area using the palm.
- An increase in temperature on the applied surface indicates that the product is activated.
- 3-5 minutes after application, the surface is smoothed with a wire brush.

All technical information stated in this product data sheet is based on laboratory tests.
Actual values may vary due to circumstances beyond our control.

İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 Işıkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35



SHOCK

■ TECHNICAL SPECIFICATIONS AND PERFORMANCE VALUES

Product Structure	Cement- based powder
Colour	Grey
Setting Time	5-10 sec.
Reaction to Fire Class	A1

The stated times apply for 20°C substrate and ambient temperature; increase at lower temperatures and decrease at higher temperatures. DRYFIX is not responsible for the application errors arising from use of product beyond its intended purpose of failure to comply with the forgoing application conditions and advice on the product.

■ SAFETY PRECAUTIONS

During use and storage, appropriate work clothes, glasses, gloves and masks should be used for worker health and safety. Eye, mouth and skin contact should be avoided. The contacted area should be washed with plenty of water. In more dangerous situations or if the product is swallowed, a specialist doctor should be consulted immediately. Food and drink should not be allowed into application areas. It should be kept out of reach of children. For detailed information, the Safety Data Sheet (SDS) should be consulted.

■ LEGAL WARNING

Applications that may occur if the product is used for purposes other than its intended purpose or if the above-mentioned conditions are not complied with: from the mistakes of İzersan Yapı Malz. San. VE TİC. LTD. ŞTİ. is not responsible.

All technical information stated in this product data sheet is based on laboratory tests. Actual values may vary due to circumstances beyond our control.

İZERSAN YAPI MALZ.SAN VE TİC.LTD.ŞTİ.

Center Factory: Egemenlik Mah. 6016/6 Sk. No:19/1 Işikkent Bornova/ İZMİR

www.dryfix.com.tr - info@izersan.com.tr

Tel&Fax: +90 850 777 05 35

